

Date:
February 18, 2009

Report #
K-418157

High Current Test Laboratory
Kinectrics Inc., Canada
Test Summary



Client

ArcWear.com

Fabric description

TecasafePlus 700 7 oz, Khaki, measured 7.6 oz/yd² over
DuPont Protera, Blue, 6.5 oz/yd² measured 6.8 oz/yd²

Reference Standard

ASTM F1959/F1959M-06ae1 Standard Test Method for Determining the Arc Rating of Materials for Clothing

Test Parameters:

Test current: 8kA	Number of samples analysed: 21
Distance to Fabric: 12 inches	Incident Energy Range: 10 to 27 cal/cm ²
Arc Gap: 12 inches	

Summary

The arc rating of this material is intended for use as flame resistant clothing for workers exposed to electric arcs. The material used in this test method are in the form of flat specimens, actual performance of the complete garment may vary depending on the final design and assembly of the garment. This test method does not apply to the electrical contact or electrical shock hazard.

Based on the data obtained and analysed in accordance with the latest version of the applicable standards, the following Arc Rating was calculated.

Arc Thermal Performance Value, ATPV = 21.7 Cal/cm²
Heat Attenuation Factor, HAF = 86.5%

The measured data and observations of the test samples after the arc exposure were collected and summarized in the attached table. The graphs and statistics on the attached sheets provide more detailed information to better understand the Arc Rating assigned to this item. The client shall review this full report, the video recordings of the arc exposure and the photographs of the samples after the test to determine if the material meets the intended specification.

Test performed by:

Hugh Hoagland
ArcWear.com
(502)314-7158
hugh@arcwear.com




ASTM F1959/F1959M-06ae1
Standard Test Method for Determining the Arc Rating of Materials for Clothing



Client: ArcWear.com

Fabric: TecasafePlus 700 7 oz, Khaki, measured 7.6 oz/yd² over
Description: DuPont Protera, Blue, 6.5 osy measured 6.8 oz/yd²

Determination of ATPV, 50% Probability of 2nd Degree Burn




ATPV = 21.7 cal/cm²

Probability of Burn	Ei
5%	16.9
10%	18.1
20%	19.5
30%	20.3
40%	21.0
50%	21.7
60%	22.4
70%	23.1
80%	23.9
90%	25.3

- # Pts = 21
- # Pts above Stoll = 5
- # Pts Break-Open = 0
- # Pts always >STOLL = 3
- # Pts always <STOLL = 9
- # Pts within 20% = 11
- # Pts in mix zone = 9

Determination of Heat Attenuation Factor



HAF = 86.5 %

Confidence Intervals
95% CI = 85.5 , 87.6

- Data pts
- Best Fit
- 95% CI
- 95% CI pts

ASTM F1959/F1959M-06ae1
Standard Test Method for Determining the Arc Rating of Materials for



Client: ArcWear.com

Fabric Description: TecasafePlus 700 7 oz, Khaki, measured 7.6 oz/yd² over DuPont Protera, Blue, 6.5 osy measured 6.8 oz/yd²

	Test #	Panel	Cycles # (60Hz)	Ei cal/cm ²	SCD cal/cm ²	HAF %	Burn yes/no	Break Open Y/N	After Flame sec.	Omit Y/N	Comment	Ignition T-shirt
1	09-508	A	13.1	10.78	-0.85	86.3	No	-	0	No		
2	09-508	B	13.1	10.66	-0.58	82.2	No	-	0	No		
3	09-508	C	13.1	10.12	-0.76	83.9	No	-	0	No		
4	09-509	A	17.2	13.26	-0.48	83.7	No	-	0	No		
5	09-509	B	17.2	13.50	-0.46	84.0	No	-	0	No		
6	09-509	C	17.2	13.10	-0.46	83.5	No	-	0	No		
7	09-510	A	21.2	14.55	-0.18	83.0	No	-	0	No		
8	09-510	B	21.2	17.26	-0.47	88.2	No	-	0	No		
9	09-510	C	21.2	14.89	-0.14	82.9	No	-	0	No		
10	09-511	A	25.1	17.85	0.13	84.5	Yes	-	0	No		
11	09-511	B	25.1	19.05	-0.12	87.5	No	-	0	No		
12	09-511	C	25.1	18.48	-0.12	87.4	No	-	0	No	Ablation	
13	09-512	A	28.1	21.01	-0.56	90.4	No	-	0	No		
14	09-512	B	28.1	20.33	-0.42	89.5	No	-	0	No		
15	09-512	C	28.1	20.60	0.01	87.6	Yes	-	0	No		
16	09-513	A	34.1	26.76	0.22	90.3	Yes	-	0	No	Ablation	
17	09-513	B	34.1	23.92	0.16	89.6	Yes	-	0	No	Ablation	
18	09-513	C	34.1	25.41	0.40	86.2	Yes	-	0	No	Ablation	
19	09-514	A	26.1	20.52	-0.40	89.4	No	-	0	No		
20	09-514	B	26.1	18.74	-0.33	87.8	No	-	0	No		
21	09-514	C	26.1	20.82	-0.30	89.1	No	-	0	No	Ablation	
22												
23												
24												
25												
26												
27												
28												
29												
30												
31												
32												
33												
34												
35												
36												